



# SANCO Sun® COMBI

Sun protection

Glass type	Glass structure	U <sub>g</sub> value to DIN EN 673	Light transmission	Total energy transmittance to DIN EN 410	Light reflection outside	Weight	Element thickness
	mm	W/m <sup>2</sup> K	LT % (±2)	g value % (±2)	LR % (±2)	kg/m <sup>2</sup>	mm (approx.)
SANCO Sun COMBI Neutral 40/21	6 - 16AR - 4	1,1	40	22	11	25	26
SANCO Sun COMBI Neutral 50/25	6 - 16AR - 4	1,1	50	27	12	25	26
SANCO Sun COMBI Neutral 61/32	6 - 16AR - 4	1,1	61	34	13	25	26
SANCO Sun COMBI Neutral 70/35	6 - 16AR - 4	1,1	70	37	14	25	26
SANCO Sun COMBI Silver 43/27	6 - 16AR - 4	1,1	44	28	45	25	26
SANCO Sun COMBI T Silver 48	6 - 16AR - 4	1,1	48	35	45	25	26

SANCO Sun COMBI coating on item 2

AR = argon

For dimensional tolerances and production possibilities see appropriate valid price list.

Excerpt from the total production range, further models on request.

Based on the SILVERSTAR SUNSTOP COMBI coating made by Glas Trösch

The technical data listed here conforms to the current values at the time of going to print and can alter without prior notice. The technical values are based on the suppliers' information or were ascertained in the course of tests by an independent testing institution in accordance with the respectively valid standards. The function values are based only on test specimens in the dimensions provided for testing. No further guarantee for technical values shall be accepted, in particular if tests are performed in other installation situations or if subsequent measurements are obtained in the building. During installation, the current version of the SANCO glazing guidelines must be followed without fail. SANCO is a trademark. Date: 04/2008